



GWENDOLYN BROOKS PAPERS TREATMENT RECORD


Treatment No.		Barcode	
Treatment by	Yungjin Shin	Treatment Date	January 27, 2022



Before Treatment	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%;">Item #</td> <td>S02-SS05-B013-F07</td> </tr> <tr> <td>Writings</td> <td> <ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "FRESH VEGETABLES" note </td> </tr> <tr> <td>Material</td> <td>Paper</td> </tr> <tr> <td>Physical Description</td> <td>Black pen writing on white paper</td> </tr> <tr> <td>Condition</td> <td>Long horizontal tear on the center of the paper.</td> </tr> </table>	Item #	S02-SS05-B013-F07	Writings	<ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "FRESH VEGETABLES" note 	Material	Paper	Physical Description	Black pen writing on white paper	Condition	Long horizontal tear on the center of the paper.
Item #	S02-SS05-B013-F07										
Writings	<ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "FRESH VEGETABLES" note 										
Material	Paper										
Physical Description	Black pen writing on white paper										
Condition	Long horizontal tear on the center of the paper.										
After Treatment	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%;">Treatment</td> <td> <ul style="list-style-type: none"> • Mended tear using remoistenable Tengujo tissue. - Wheat starch paste coated Tengujo (5gsm), reactivated by gellan gum (10% ethanol). • Housed in polyester L-sleeve. </td> </tr> <tr> <td>Treatment Hours</td> <td>0.5 hour</td> </tr> </table>	Treatment	<ul style="list-style-type: none"> • Mended tear using remoistenable Tengujo tissue. - Wheat starch paste coated Tengujo (5gsm), reactivated by gellan gum (10% ethanol). • Housed in polyester L-sleeve. 	Treatment Hours	0.5 hour						
Treatment	<ul style="list-style-type: none"> • Mended tear using remoistenable Tengujo tissue. - Wheat starch paste coated Tengujo (5gsm), reactivated by gellan gum (10% ethanol). • Housed in polyester L-sleeve. 										
Treatment Hours	0.5 hour										

Before Treatment	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 15%;">Item #</td> <td>S02-SS05-B013-F07</td> </tr> <tr> <td>Writings</td> <td> <ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "MENU" note </td> </tr> <tr> <td>Material</td> <td>Paper</td> </tr> <tr> <td>Physical Description</td> <td>Black and red pen writing on a printed scrap paper</td> </tr> <tr> <td>Condition</td> <td>Long horizontal tear on the center of the paper.</td> </tr> </table>	Item #	S02-SS05-B013-F07	Writings	<ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "MENU" note 	Material	Paper	Physical Description	Black and red pen writing on a printed scrap paper	Condition	Long horizontal tear on the center of the paper.
Item #	S02-SS05-B013-F07										
Writings	<ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "MENU" note 										
Material	Paper										
Physical Description	Black and red pen writing on a printed scrap paper										
Condition	Long horizontal tear on the center of the paper.										

<p style="text-align: center;">After Treatment</p> 	<p>Treatment</p>	<ul style="list-style-type: none"> Mended tear using remoistenable Tengujo tissue. - Wheat starch paste coated Tengujo (5gsm), reactivated by gellan gum (10% ethanol). Housed in polyester L-sleeve.
	<p>Treatment Hours</p>	<p>0.5 hour</p>

<p style="text-align: center;">Before Treatment</p> 	<p>Item #</p>	<p>S02-SS05-B013-F07</p>
	<p>Writings</p>	<ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "DINNER MENU" note
	<p>Material</p>	<p>Paper</p>
	<p>Physical Description</p>	<p>Black pen writing on white paper</p>
	<p>Condition</p>	<p>Long horizontal tear on the center of the paper.</p>

<p style="text-align: center;">After Treatment</p> 	<p>Treatment</p>	<ul style="list-style-type: none"> Mended tear using remoistenable Tengujo tissue. - Wheat starch paste coated Tengujo (5gsm), reactivated by gellan gum (10% ethanol). Housed in polyester L-sleeve.
	<p>Treatment Hours</p>	<p>0.5 hour</p>

<p style="text-align: center;">Before Treatment</p> 	<p>Item #</p>	<p>S02-SS05-B013-F21</p>
	<p>Writings</p> <ul style="list-style-type: none"> - Notes/Jottings - "Labeled A-Ph" - "Pecord(?)..." note 	
	<p>Material</p>	<p>Paper</p>
	<p>Physical Description</p>	<p>Black and blue pen writing on brown paper</p>
	<p>Condition</p>	<p>Small tear with creases on bottom right corner and top right corner. Brittle paper.</p>
<p style="text-align: center;">After Treatment</p> 	<p>Treatment</p>	<ul style="list-style-type: none"> • Mended tear using remoistenable Tengujo tissue. - Wheat starch paste coated Tengujo (5gsm), reactivated by gellan gum (10% ethanol). • Housed in polyester L-sleeve.
	<p>Treatment Hours</p>	<p>0.5 hour</p>